

OK Tigrod 347Si

Bare corrosion resisting chromium-nickel rods for welding of austenitic chromium nickel alloys of 18 % Cr-8 % Ni-type.

OK Tigrod 347Si has a good general corrosion resistance. The alloy is stabilized with Niobium to improve the resistance against intergranular corrosion of the weld metal. The higher silicon content improves the welding properties, such as wetting. Due to the niobium content this alloy is recommended for use at higher temperatures.

Классификации	AWS A5.9 : ER347Si EN ISO 14343-A : W 19 9 NbSi
Тип сплава	Austenitic (with approx. 8 % ferrite) 19% Cr - 9% Ni - Nb
Защитный газ	I1 (EN ISO 14175)

Типичные свойства образца с V-образным надрезом по Шарпи

Состояние	Температура испытания	Работа удара
После сварки	20 °C	113 J

Хим. состав наплавленного металла

C	Mn	Si	S	P	Ni	Cr	Mo	Cu	Nb
0.04	1.5	0.8	0.01	0.02	10	20	0.1	0.1	0.7

Хим. состав проволоки

C	Mn	Si	Ni	Cr	Mo	Cu	Nb
0.04	1.7	0.7	9.8	19	0.1	0.10	0.60