

OK Autrod 317L

A continuous solid corrosion resisting chromium-nickel-molybdenum wire for welding of austenitic stainless alloys of 19% Cr 13% Ni 3% Mo types.
OK Autrod 317L has a good resistance to general corrosion and pitting due to its high content of molybdenum. The alloy has a low carbon content which makes this alloy particularly recommended where there is a risk of intergranular corrosion. The alloy is used in severe corrosion conditions such as in the petrochemical, pulp and paper industries.

Классификация сварочной проволоки	SFA/AWS A5.9 : ER317L EN ISO 14343-A : G 18 15 3 L
--	---

Тип сплава	Austenitic (with approx. 8 % ferrite)
Защитный газ	M12, M13 (EN ISO 14175)

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
После сварки	20 °C	135 J
После сварки	-196 °C	55 J

Хим. состав проволоки

C	Mn	Si	Ni	Cr	Mo	N	FN WRC-92
0.01	1.4	0.4	13.6	18.9	3.6	0.05	7

Данные наплавки

Диаметр	Ток	B	Скорость подачи проволоки	Коэффиц. наплавки
0.8 mm	50-140 A	16-22 V	3.4-11.0 m/min	0.8-2.7 kg/h
1.0 mm	80-190 A	16-24 V	2.6-7.1 m/min	0.9-2.7 kg/h
1.2 mm	180-280 A	20-28 V	4.9-8.5 m/min	2.6-4.5 kg/h
1.6 mm	230-350 A	24-28 V	3.2-5.5 m/min	3.0-5.2 kg/h