

## OK Autrod 2209 SAW

A continuous solid corrosion resisting Duplex wire for welding of austenitic-ferritic stainless alloys of 22% Cr, 5% Ni, 3% Mo types.

OK Autrod 2209 has a high general corrosion resistance. In media containing chloride and hydrogen sulphide the alloy has a high resistance to intergranular, pitting and especially to stress corrosion. The alloy is used in a variety of applications across all industrial segments.

OK Autrod 2209 can be used in combination with OK Flux 10.93 or OK Flux 10.94.

<b>Классификация сварочной проволоки</b>	SFA/AWS A5.9 : ER2209 EN ISO 14343-A : S 22 9 3 N L
<b>Одобрения</b>	CE EN 13479 VdTUV 12101 NAKS/HAКC 3.2-4.0mm

Одобрения на материалы выдаются с привязкой к заводу изготовителю. Подробную информацию можно получить в представительствах ESAB.

<b>Тип сплава</b>	Austenitic-ferritic (22.5 % Cr - 8 % Ni - 3 % Mo - Low C)
-------------------	---

### Хим. состав проволоки

C	Mn	Si	Ni	Cr	Mo	N	PRE	FN WRC-92
0.01	1.5	0.5	8.5	22.7	3.2	0.17	35	55